



# **Coupling Agent**

#### KH-540 Silane coupling agent

KH-540 Silane coupling agent		
FEATURE	<ul> <li>Excellent adhesion promoters</li> <li>Increase the compression resilience</li> <li>Improve strength and moisture resistance</li> <li>Improve the filler in the polymer wetting and dispersion</li> <li>Improve the physical and mechanical reinforced plastic dry and wet bending strength, compressive strength, shear strength, etc.</li> <li>Enhance the cohesion and improve the mechanical, electrical, water resistance, anti-aging properties</li> <li>Improve the dispersion of pigment and increase of glass, aluminum, ferrous metal adhesion</li> </ul>	
TYPE	$\gamma$ - aminopropyl trimethoxysilane	
TYPICAL PROPERTIES	Appearance:	colorless transparent liquid
	Content:	≥97%
	Flash point:	<b>110℃</b>
	<b>Boiling point:</b>	≥290℃
	Molecular	179
	Weight:	
	Density:	1.005-1.025g/cm <sup>3</sup>
	CAS Number:	13822-56-5
	Refractive index:	ND25 1.420-1.430
	Structural	NH2(CH2)3Si(OCH3)3
	formula:	
	Corresponding trademark:	A-1110(Union Carbide); Z-6011(Dow Corning); KBM-903(Shin-Etsu)
	Solubility:	Silane coupling agent KH-540 is a kind of
	Solubility.	reactive silane coupling agent. Soluble in
		benzene, ethyl acetate and other organic
		solvents, easily to hydrolysis and
		crosslinking reaction

#### **APPLICATION**

 It can be used as a variety of mineral-filled polymer viscosity and accelerators

Anhui Sinograce Chemical Co., Ltd. Tel: +86-0551-63459511

Email: sales@sinogracechem.com

Add.: Hefei city, Anhui province, China

Mob: +86 15855525589

### SINOGRACE

## **COUPLING AGENT**

**The Chemical Company** 

# STORAGE AND HANDLING

- Available in 25 kg/drum
- Store products in tightly closed original containers at  $5-40^{\circ}\text{C}$
- Shelf life: 12 months from delivery date
- According to non-dangerous goods transport

Anhui Sinograce Chemical Co., Ltd. Add.: Hefei city, Anhui province, China Tel: +86-0551-63459511 Mob: +86 15855525589

Email: sales@sinogracechem.com