## **FLUORO CHEMICAL**



## **Fluororesin**

## PF-320 Marine ship anti-corrosion and antifouling coating

## DESCRIPTION

PF-320 is specifically developed for ship marine coatings. It is composed of CTFE/PTFE copolymer resin with excellent salty foggy resistant, outstanding weatherabiltiy, good antifouling, abrasion resistant and excellent corrosion resistant.

| TYPE            | Fluoropolymer (CTFE/PTFE copolymer)  |   |
|-----------------|--|---|
| KEY<br>FEATURES | <ul> <li>Variety of gloss</li> <li>Excellent salty foggy resistant and weatherability</li> <li>Excellent strong acid resistant and alkali resistant</li> <li>Good antifouling and excellent corrosion resistant</li> </ul> |   |
|                 | Appearance   | Customized color                          |
|                 | Solid content (%)  | 50±2                                      |
|                 | Density (g/cm <sup>3</sup> )   | 1.1-1.3                                   |
|                 | Viscosity (MPa s)  | 1200-2500                                 |
|                 | Gloss  | 20-80                                     |
|                 | Hardness   | 2-3H                                      |
| <b>TYPICAL</b>  | Solvent  | Butyl acetate                             |
| PROPERTIES      | 15% H2SO4 (dipping 360 days)   | No blistering, no rust and no peeling off |
|                 | 15% NaOH (dipping 7 days)  | No blistering, no rust and no peeling off |
|                 | Salt foggy resistant (5000h)   | No blistering, no rust and no peeling off |
|                 | Salt water resistant (3000h)   | No blistering, no rust and no peeling off |
| APPLICATION     | <ul><li>Marine ship</li><li>Yacht</li></ul>  |   |
| STORAGE         | • Available in 200 kg/ barrel or 20 kg/ barrel   |   |
| AND             | <ul> <li>Store products in tightly closed original containers at 5-40°C</li> <li>Shelf life: 12 months from delivery date</li> </ul>   |   |
| HANDLING        | <ul> <li>According to non-dangerous goods transport</li> </ul>   |   |

Anhui Sinograce Chemical Co., Ltd. Tel: +86-0551-63459511

Email: sales@sinogracechem.com

Add.: Hefei city, Anhui province, China

Mob: +86 15855525589